



İSTANBUL ÜNİVERSİTESİ
Mühendislik Fakültesi
Kimya Mühendisliği Bölümü



Sayı: B.30.2.İST.0.17.81.00/693 / 2056

24 08 2015

Expression of the results	Maximum admissible concentration	Tardigrade ECTR 200	
		Concentration in final extract after 24 hours	Concentration in final extract after 7 days
Aluminium (Al), µg/L	≤200	99	99
Antimony (Sb), µg/L	≤5	<5	<5
Arsenic (As) miktarı, µg/L	≤10	<10	<10
Baryum (Ba), µg/L	≤1000	<10	<10
Cadmium (Cd), µg/L	≤5	<5	<5
Chromium (Cr), µg/L	≤50	<10	<10
Iron (Fe), µg/L	≤200	108	108
Lead (Pb), µg/L	≤25	<10	<10
Manganese (Mn), µg/L	≤50	<10	<10
Mercury (Hg), µg/L	≤1	<1	<1
Nickel (Ni), µg/L	≤20	<10	<10
Selenium (Se), µg/L	≤10	<10	<10

Tardigrade ECTR 200 , have been found to comply with the requirements of BS 6920 Part 1 clause 8.



Prof. Dr. İsmail AYDIN
Istanbul University
Engineering Faculty
Chemical ENgineering Department