



ISTANBUL UNIVERSITY  
Engineering Faculty  
Chemical Engineering Department



Sayı: B.30.2.İST.0.17.81.00/693 / 2056

29.10.2014

**TARDIGRADE ECSP 260**

Two Component, Solvent Free, , Epoxy Resin Based Floor and Wall Paint

**Product Information:**

**Appearance / Color**

Resin – part A : gray, liquid  
Hardener – part B : pale yellow, liquid

**Technical Information:**

**Chemical Structure :** Epoxy

**Density (ASTM D792 / ISO 1183 / DIN 53479)**

Resin – part A : 1.840 kg/l  
Hardener – part B : 1.020 kg/l  
Mixed resin A + B : 1.640 kg/l

**Viscosity (ASTM D2555 / ISO 2555 / DIN EN ISO 2555)**

Resin – part A : 24000 mPa·s  
Hardener – part B : 440 mPa·s  
Mixed resin A + B : 3500 mPa·s

**Water Absorption (ASTM D570-98 / ISO 62 / DIN 53495)**

– (0.001%).

**Pot Life**

65 minute (23 °C).



34320 Avcılar/ISTANBUL Tel: +90 212 473 70 70 Fax: +90 212 473 71 80

Prof. Dr. İsmail AYDIN  
BSc, DIC, PhD



## TARDIGRADE ECSP 260

Two Component, Solvent Free, , Epoxy Resin Based Floor and Wall Paint

### Mechanical / Physical Properties

TEST	METHOD			VALUE		
				Average	Maximum	Minimum
Compressive strength	ASTM D695	ISO 604	DIN 53454	60 MPa	67 MPa	58 MPa
Flexural strength	ASTM D790	ISO 178	DIN 53452	30.87 MPa	37.53 MPa	26.67 MPa
Maximum force	ASTM D638	ISO 527	DIN 53457	385 N	393 N	371 N
% elongation at break	ASTM D638	ISO 527	DIN 53457	23.11%	28.26%	20.89%
Bond strength	ASTM D4541	ISO 4624	DIN 4624	12.05 MPa	16.01 MPa	9.97 MPa
Shore D hardness	ASTM D2240	ISO 868	DIN 53505	80	84	77

Test results for Tardigrade ECSP 260 Two Component, Solvent Free, , Epoxy Resin Based Floor and Wall Paint.





## TARDIGRADE ECSP 260

Two Component, Solvent Free, , Epoxy Resin Based Floor and Wall Paint

### Chemical Resistance

Chemicals	Values
HYDRCHLORIC ACID 25%	2
HYDRCHLORIC ACID 10%	3
NITRIC ACID 25%	2
NITRIC ACID 10%	3
FORMIC ACID 25%	2
FORMIC ACID 10%	3
ASETIC ACID 25%	3
ASETIC ACID 10%	3
SULFURIC ACID 25%	3
SULFURIC ACID 10%	3
LACTIC ACID 25%	3
LACTIC ACID 10%	3
ETHYL ALCOHOL	3
AMMONIA	3
PERCHLOROETHYLENE	3
DIESEL FUEL	3
ACETONE	3
FUEL THINNER	3
HYDRAULIC OIL	3
THINNER	3

Excellent 3 Good 2  
Low 1 Not resistant 0

Prof. Dr. İsmail AYDIN  
Istanbul University  
Engineering Faculty  
Chemical Engineering Department



Prof. Dr. İsmail AYDIN  
BSc, DIC, PhD