



ISTANBUL UNIVERSITY  
Engineering Faculty  
Chemical Engineering Department



Sayı: B.30.2.İST.0.17.81.00/693 / 2056

29.10.2014

**TARDIGRADE PCAP 730**

Two Component , Solvent Based, Semi Glossy Finish, Self-Leveling, UV Resistant,  
Aliphatic, Polyurethane Topcoat

**Product Information:**

**Appearance / Color**

Resin – part A : gray, liquid  
Hardener – part B : transparent, liquid

**Technical Information**

**Chemical Structure :** Polyurethane

**Density (ASTM D792 / ISO 1183 / DIN 53479)**

Resin – part A : 1.330 kg/l  
Hardener – part B : 1.080 kg/l  
Mixed resin A + B : 1.260 kg/l

**Viscosity (ASTM D2555 / ISO 2555 / DIN EN ISO 2555)**

Resin – part A : 1550 mPa·s  
Hardener – part B : 620 mPa·s  
Mixed resin A + B : 1330 mPa·s

**Water Absorption (ASTM D570-98 / ISO 62 / DIN 53495)**

- (0.002%).

**Pot Life**

4 hours (23 °C).

34320 Avcılar/İSTANBUL Tel: +90 212 473 70 70 Fax: +90 212 473 71 80



Prof. Dr. İsmail AYDIN  
BSc, DIC, PhD



ISTANBUL UNIVERSITY  
Engineering Faculty  
Chemical Engineering Department



Sayı: B.30.2.İST.0.17.81.00/693 / 2056

29.10.2014


**TARDIGRADE PCAP 730**

Two Component , Solvent Based, Semi Glossy Finish, Self-Leveling, UV Resistant,  
Aliphatic, Polyurethane Topcoat

**Mechanical / Physical Properties**

TEST	METHOD			VALUE		
				Average	Maximum	Minimum
Compressive strength	ASTM D695	ISO 604	DIN 53454	-	-	-
Flexural strength	ASTM D790	ISO 178	DIN 53452	-	-	-
Maximum force	ASTM D638	ISO 527	DIN 53457	-	-	-
% elongation at break	ASTM D638	ISO 527	DIN 53457	-	-	-
Bond strength	ASTM D4541	ISO 4624	DIN 4624	-	-	-
Shore D hardness	ASTM D2240	ISO 868	DIN 53505	75	77	72

Test results for Tardigrade PCAP 730 Two Component , Solvent Based, Semi Glossy Finish, Self-Leveling, UV Resistant, Aliphatic, Polyurethane Topcoat.



320 Avcılar/İSTANBUL Tel: +90 212 473 70 70 Fax: +90 212 473 71 80

Prof. Dr. Ismail AYDIN  
BSc, DIC, PhD



ISTANBUL UNIVERSITY  
Engineering Faculty  
Chemical Engineering Department



Sayı: B.30.2.İST.0.17.81.00/693 / 2056

29.10.2014

**TARDIGRADE PCAP 730**

Two Component , Solvent Based, Semi Glossy Finish, Self-Leveling, UV Resistant,  
Aliphatic, Polyurethane Topcoat

**Chemical Resistance**

Chemicals	Values
HYDRCHLORIC ACID 25%	2
HYDRCHLORIC ACID 10%	3
NITRIC ACID 25%	2
NITRIC ACID 10%	2
FORMIC ACID 25%	2
FORMIC ACID 10%	3
ASETIC ACID 25%	3
ASETIC ACID 10%	3
SULFURIC ACID 25%	3
SULFURIC ACID 10%	3
LACTIC ACID 25%	3
LACTIC ACID 10%	3
ETHYL ALCOHOL	3
AMMONIA	3
PERCHLOROETHYLENE	3
DIESEL FUEL	3
ACETONE	3
FUEL THINNER	3
HYDRAULIC OIL	3
THINNER	3

Excellent 3 Good 2  
Low 1 Not resistant 0

Prof. Dr. İsmail AYDIN  
Istanbul University  
Engineering Faculty  
Chemical Engineering Department



34320 Avcılar/İSTANBUL Tel: +90 212 473 70 70 Fax: +90 212 473 71 80

Prof. Dr. İsmail AYDIN  
BSc, DIC, PhD