



TARDIGRADE PRGF 900

Two Component, Solvent Free, Polyurethane Based Filling Mortar

Product Information:

Appearance / Color

Resin – part A : gray, liquid
Hardener – part B : red brown, liquid

Technical Information

Chemical Structure : Polyurethane

Density (ASTM D792 / ISO 1183 / DIN 53479)

Resin – part A : 1.390 kg/l
Hardener – part B : 1.200 kg/l
Mixed resin A + B : 1.350 kg/l

Viscosity (ASTM D2555 / ISO 2555 / DIN EN ISO 2555)

Resin – part A : 7000 mPa·s
Hardener – part B : (DIN CUP 4) 13 s
Mixed resin A + B : 3300 mPa·s

Water Absorption (ASTM D570-98 / ISO 62 / DIN 53495)

– (0.002%).

Pot Life

90 minutes (23 °C).





TARDIGRADE PRGF 900

Two Component, Solvent Free, Polyurethane Based Filling Mortar

Mechanical / Physical Properties

TEST	METHOD			VALUE		
				Average	Maximum	Minimum
Compressive strength	ASTM D695	ISO 604	DIN 53454	-	-	-
Flexural strength	ASTM D790	ISO 178	DIN 53452	-	-	-
Maximum force	ASTM D638	ISO 527	DIN 53457	230 N	237 N	221 N
% elongation at break	ASTM D638	ISO 527	DIN 53457	200%	218%	193%
Bond strength	ASTM D4541	ISO 4624	DIN 4624	3.15 MPa	3.19 MPa	3.02 MPa
Shore A hardness	ASTM D2240	ISO 868	DIN 53505	80	82	77

Test results for Tardigrade PRGF 900 Two Component, Solvent Free, Polyurethane Based Filling Mortar.





ISTANBUL UNIVERSITY
Engineering Faculty
Chemical Engineering Department



Sayı: B.30.2.İST.0.17.81.00/693 / 2056

29.10.2014

TARDIGRADE PRGF 900

Two Component, Solvent Free, Polyurethane Based Filling Mortar

Chemical Resistance

Chemicals	Values
HYDRCHLORIC ACID 25%	2
HYDRCHLORIC ACID 10%	3
NITRIC ACID 25%	2
NITRIC ACID 10%	2
FORMIC ACID 25%	3
FORMIC ACID 10%	3
ASETIC ACID 25%	3
ASETIC ACID 10%	3
SULFURIC ACID 25%	3
SULFURIC ACID 10%	3
LACTIC ACID 25%	3
LACTIC ACID 10%	3
ETHYL ALCOHOL	3
AMMONIA	3
PERCHLOROETHYLENE	3
DIESEL FUEL	3
ACETONE	3
FUEL THINNER	3
HYDRAULIC OIL	3
THINNER	3

Excellent 3 Good 2
Low 1 Not resistant 0



Prof. Dr. İsmail AYDIN
Istanbul University
Engineering Faculty
Chemical Engineering Department

34320 Avcılar/ISTANBUL Tel: +90 212 473 70 70 Fax: +90 212 473 71 80

Prof. Dr. İsmail AYDIN
BSc, DIC, PhD